

Polycarbonate

† . .

(2000 12 9)

Solvent Induced Crystallization of Polycarbonate in Mixed Solvent

D. K. Hwang[†], C. Y. Lee, and Y. G. Shul

Department of Chemical Engineering, Yonsei University, Seoul, Korea

†e-mail : HDK1024@yahoo.co.kr

(Received December 9, 2000)

: bisphenol A polycarbonate(PC)
chloroform , isopropanol
PC SEM, XRD, DSC , DSC XRD
PC PC
PC
75/25 wt% PC 가 PC powder
(9.85)가 PC (9.9)

ABSTRACT : Crystallization behaviour of bisphenol A polycarbonate(PC) from amorphous phase was studied by varying solvent/nonsolvent ratios in liquid phase. Chloroform and isopropanol were used as a solvent and a nonsolvent, respectively. Samples were characterized by optical microphotography, scanning electron microscope(SEM), X-ray diffraction (XRD), and differential scanning calorimeter(DSC). DSC and XRD measurement were used to determine the crystallinity of PC. The solubility constant seems to be critical to control the PC crystallinity in solvent/nonsolvent mixture. The difference in PC crystallinity is explained by the difference in solubility constant of the mixture depending on the solvent/nonsolvent ratio. PC solution of 75/25 wt% (solvent/nonsolvent) ratio produced PC powder showing maximum crystallinity. At this condition solubility constant (9.85) of the mixed solvent was close to PC(9.9).

Keywords : polycarbonate, crystalline, amorphous, solubility parameter.

PC 가 ,
Polycarbonate(PC) 20 PC
가
engineering plastic ,
PC 가 .²
.¹ PC

PC
X-ray
bisphenol A polycarbonate
가, XRD, DSC, NMR
4-7 AFM(atomic force micro-
scope) SPM(scanning force microscope)

가 Harron HR 8,9
R. C. Ruaan 13

가
가
PC
가, PC

chloroform(Junsei Co.),
isopropanol(Hyaman Co.), PC
Mitsubishi-Dow Chemical 201-10
PC ($\overline{M}_w$)
40800 GPC(gel permeation chromatography,
Water's, 150CV, USA)

PC가
Figure 1 PC
Process A chloro-
form PC 10 phr (wt%) 가




Figure 1. Procedure of solvent induced crystallization of PC.

60 60
Process B isopropanol
Process PC PC
가 30, 24
90
PC (optical
microphotography, Nikon, SM2T, Japan)
(scanning electron microscope, Jeol, H-
6010A, Japan)
X
(Rigaku, D-max3, Japan) $2\theta = 3^\circ$ 30°
CuK α
10 /min 50
350 (dif-
ferential scanning calorimeter, DuPont, TA ins-
trument, USA)

PC
Figure 2
(a)

Polycarbonate




Figure 2. Surface morphology of PC samples : PC in (a) CH_2Cl_2 , (b) CHCl_3/IPA (95/5 wt%), (c) CHCl_3/IPA (80/20 wt%), (d) CHCl_3/IPA (75/25 wt%), (e) CHCl_3/IPA (70/30 wt%), and (f) IPA.

PC , (b) PC
PC . , PC가
isopropanol 5 wt% . 20 wt% (c)




Figure 3. XRD patterns of PC samples :(a) amorphous PC, (b) crystallized PC in CHCl₃/IPA(95/ 5 wt%), and (c) crystallized PC in CHCl₃/IPA(75/25 wt%).





Figure 4. Effect of solubility parameter on PC crystallinity.



814




Table 1. Effect of Solubility Parameters on PC Morphology

solvent chloroform ratio(wt%)	nonsolvent isopropanol ratio(wt%)	*solubility parameter (cal/cm ³) ^{1/2}	PC morphology after drying
		mixed solvent	
100	0	9.30	transparent film
95	5	9.41	opaque film
85	15	9.63	opaque power + film
80	20	9.74	opaque powder
75	25	9.85	opaque powder
70	30	9.96	opaque powder + mass
65	35	10.07	opaque mass
55	45	10.29	opaque mass
0	100	11.50	transparent pellet

*Solubility parameter((cal/cm³)^{1/2} ; solvent ratio×solvent solubility parameter (9.30) +nonlvent ratio×nonsolvent solubility parmeter (11.5)).

PC , powder

Table 1

¹² PC 9.9 9.3

chloroform 11.5

isopropanol

PC

95/5, 75/25, 55/45 wt%

9.41, 9.85, 10.29

가 9.41

PC 가

PC 가 45.2%

가 10.29 63.5%

PC 가

가 PC가

가 9.85 PC

9.9 가

4 - 7 μm powder 가 PC가

PC




Figure 5. DSC thermograms of PC samples : (a) amorphous PC, (b) crystallized PC in CH₃Cl/IPA (95/5 wt%), (c) crystallized PC in CH₃Cl/IPA(80/20 wt%), and (d) crystallized PC in CH₃Cl/IPA(75/25 wt%), and (e) crystallized PC in CH₃Cl/IPA(70/30 wt%).

Figure 5




Figure 6. A polycarbonate in the (a)amorphous and (b)crystallized state[H. Schell, *Chemistry and Physics of Polycarbonate*, 136 (1964)].

PC	(a)	142.8	154.0		PC
	151.8		(T _g)		
			T _g		
		200	250		
(T _m)가				75/25	75/25
wt%		(d)		wt%	X
		(b), (c), (e)		, DSC	30.7
240.2				J/g	PC
(d)					
PC	228.1	T _m	30.7 J/g		가 9.85
		가			가
				9.9	가
				powder	가 PC
		PC	T _m		PC
Figure 6	H. Shell				
PC			1 (a)		
		(b)		:	2001
C=O		가			21
가					
		PC가			
			PC		
		가			

1. H. Schell, "Chemistry and Physics of Polycarbonate" p.127, 1964.
2. L. L. Patrica, K. Tomasz, D. P. Mark, and S. Jacob, *Macromolecules*, 28, 2476(1995).

Polycarbonate

3. J. Dybal, P. Schmidt, J. Baldrian, and J. Katochvil, *Macromolecules*, **31**, 6611(1998).
4. C. C. Su, E. M. Woo, C. Y. Chen, and R. R. Woo, *Polymer*, **38**, 9(1997).
5. G. Ji, G. Xue, J. Ma, C. Dong, and X. Gu, *Polymer*, **37**(15), 3255(1996).
6. M. Tomaselli, M. M. Zehnder, P. Robyr, C. Grob - Pisano, R. R. Ernst, and U. W. Suter, *Macromolecules*, **30**, 3579(1997).
7. B. Montanari, P. Ballone, and R. O. Johnes, *Macromolecules*, **31**, 7784(1998).
8. H. R. Harron, R. G. Pritchard, B. C. Cope, and D. T. Goddard, *Inter. J. of Elect.*, **81**, 4(1996).
9. H. R. Harron, R. G. Pritchard, B. C. Cope, and D. T. Goddard, *J. Polym. Sci. Part B-Polym. Phys.*, **34**, 1(1996).
10. J. Bradup and E.H. Immergut, "Polymer Hand Book", vol , p. 519, 1989.
11. M. Ercken, P. Adriaenssens, D. Vanderzande, and J. Gelan, *Macromolecules*, **28**, 8541 (1995).
12. M. Terada and R. H. Marchessault, *Inter. J. Bio. Mac.*, **25**, 207(1999).
13. R. C. Ruan, T. Chang, and D. M. Wang, *J. Polym. Sci. : Part B, Polym. Phys.*, **37**, 1495(1999).
14. E. Laredo, M. Grimau, A. Muller, A. Bello, and N. Suarez, *J. Polym. Sci. : Part B, Polym. Phys.*, **34**, 2863 (1996).